

**KIMTECH™**

# Kimtech™ G3 NxT Nitrile Gloves

62990 / 62991 / 62992 / 62993 / 62994 / 62995

**DATA PACK**





# Table of Content

---

- › Declaration of Conformity<sup>(1)</sup>
- › Certificate of Analysis<sup>(2)</sup>
- › Test Method for Analysing Particle Counts
- › Test Method for Analysing Extractables
- › Packaging Components
- › Insert Extract

<sup>(1)</sup>For other languages please visit the product page on [www.kimtech.eu](http://www.kimtech.eu)

<sup>(2)</sup>Certificate of Analysis are available on a lot by lot basis, please visit [www.kimtech.eu/ressources/certificates](http://www.kimtech.eu/ressources/certificates)

# EU Declaration of Conformity

Version      Revision Date:      DoC #:      Date of last issue: -  
1.0          15.11.2022          100000020867      Date of first issue: 15.11.2022

The manufacturer, and his authorised representative established in the Community, Kimberly-Clark Europe Ltd., confirms that the PPE models, as described, are in conformity with the provisions of Regulation (EU) 2016/425 for category

| Style  | Product Code(s)                             | Product Description            |
|--------|---|--------------------------------|
| Gloves | 62990, 62991, 62992,<br>62993, 62994, 62995 | Kimtech* G3 NxT Nitrile Gloves |

## **Personal Protective Equipment, the European harmonised standard:**

Category III PPE

Subject to the procedures set out in Module D of the The Regulation (EU) 2016/425 EC under the supervision of Notified Body.

## **Harmonized Standards**

: EN ISO 21420:2020 (Protective gloves – General requirements and test methods)

EN ISO 374-1:2016+A1:2018: (Protective gloves against chemicals and micro-organisms) as a Type B glove against reagents KPT)

EN ISO 374-5:2016: (Protective gloves against chemicals and micro-organisms) with EN 374-2:2019 performance level 2 and including Viral Penetration

Is identical to the tested samples which are the subject of:

**EU type-examination certificate:** 0598/PPE/22/4248

**Granted to Kimberly - Clark Europe Ltd, based on Technical File by the Notified Body:** PPE.TG.GBL.130.v03

Signed on behalf of the manufacturer in the European Community.

|                                   |   |                              |
|-----------------------------------|---|------------------------------|
| <b>Christelle Bouvier</b>         |  | Revision Date:<br>15.11.2022 |
| Senior Regulatory Affairs Manager |   |                              |
| Kimberly-Clark Europe Ltd.        |   |                              |

As requested by the (EU) 2016/425, addresses of the parts involved as follows:

|   |                      |
|---|----------------------|
| <b>Kimberly-Clark Europe Limited</b>                                  |                      |
| Walton Oaks, Dorking Road, Tadworth, Surrey, KT20 7NS, United Kingdom |                      |
| Telephone: +44 1737 736000  | Fax: +44 1737 736670 |
| <b>SGS FIMKO OY (0598)</b>  |                      |
| Takomotie 8, HELSINKI, 00380, Finland                                 |                      |
| Telephone: +358 9 696 361   | Fax:                 |
| <b>TÜV SÜD Product Service GmbH Zertifizierstellen (0123)</b>         |                      |
| Ridlerstraße 65, MÜNCHEN, 80339, Germany,                             |                      |

# EU Declaration of Conformity

|         |                |              |                                 |
|---------|----------------|--------------|---------------------------------|
| Version | Revision Date: | DoC #:       | Date of last issue: -           |
| 1.0     | 15.11.2022     | 100000020867 | Date of first issue: 15.11.2022 |

---

|                              |      |
|------------------------------|------|
| Telephone: +49 (89) 50084261 | Fax: |
|------------------------------|------|



# UK Declaration of Conformity

Version 1.0      Revision Date: 16.11.2022      DoC #: 100000050880      Date of last issue: -  
Date of first issue: 16.11.2022

The manufacturer, and his authorised representative established in the United Kingdom, Kimberly-Clark Europe Ltd., confirms that the PPE models, as described, are in conformity with the provisions of Regulation (EU) 2016/425 as brought into UK law and amended.

| Style  | Product Code(s)                          | Product Description            |
|--------|--|--------------------------------|
| Gloves | 62990, 62991, 62992, 62993, 62994, 62995 | Kimtech* G3 NxT Nitrile Gloves |

### Personal Protective Equipment:

Category III PPE

Subject to the procedures set out in Module D of the Regulation (EU) 2016/425 as brought into UK law and amended under the supervision of Approved Body

### UK Designated Standards:

: EN ISO 21420:2020 (Protective gloves – General requirements and test methods)

EN ISO 374-1:2016+A1:2018: (Protective gloves against chemicals and micro-organisms) as a Type B glove against reagents KPT)


EN ISO 374-5:2016: (Protective gloves against chemicals and micro-organisms) with EN 374-2:2019 performance level 2 and including Viral Penetration

Is identical to the tested samples which are the subject of:

**UK type-examination certificate:**0120/PPE/221323

**Granted to Kimberly - Clark Europe Ltd, based on Technical File examination by the Approved Body:**PPE.TG.GBL.130.v03

Signed on behalf of the manufacturer in the United Kingdom.

|  |   |                              |
|--|---|------------------------------|
| <b>Liz Brigden</b>                             |  | Revision Date:<br>16.11.2022 |
| KCP EMEA Regulatory Affairs Associate Director |   |                              |
| Kimberly-Clark Europe Ltd.                     |   |                              |

As requested by the (EU) 2016/425 as brought into UK law and amended, addresses of the parts involved as follows:

|  |                      |
|--|----------------------|
| <b>Kimberly-Clark Europe Limited</b>   |                      |
| Walton Oaks, Dorking Road, Tadworth, Surrey, KT20 7NS, United Kingdom                    |                      |
| Telephone: +44 1737 736000   | Fax: +44 1737 736670 |
| <b>SGS United Kingdom Limited (0120)</b>   |                      |
| Rossmore Business Park, Ellesmere Port, South Wirral, CH65 3EN, Cheshire, United Kingdom |                      |
| Telephone: +44 (0) 1934 522917   | Fax:                 |
| <b>TUV SUD BABT UNLIMITED (0168)</b>   |                      |

# UK Declaration of Conformity

|         |                |              |                                 |
|---------|----------------|--------------|---------------------------------|
| Version | Revision Date: | DoC #:       | Date of last issue: -           |
| 1.0     | 16.11.2022     | 100000050880 | Date of first issue: 16.11.2022 |

---

|  |      |
|--|------|
| Octagon House, Concorde Way, Segensworth North, Fareham, PO15 5RL, Hampshire, United Kingdom |      |
| Telephone: +44 1489 558100   | Fax: |



Kimberly-Clark Professional\*1400 Holcomb Bridge Rd.Roswell, GA 30076 USA

## CERTIFICATE OF ANALYSIS

**Product Description :** Kimtech\* G3 NXT Cleanroom Nitrile,12"

**K-C Code :** 62990-40, 62991-40, 62992-40, 62993-40, 62994-40, 62995-40

**Lot # :** 880223  
**Batches :** SM303201X to SM305901X  
 SM303201V to SM305901V

**Total Cases per Lot :** 180  
**Date of Manufacture :** Feb-23  
**Expiration Date :** 2028-01

| Physical Test Data**       |            |                 |        |        |            |                |               |
|----------------------------|------------|-----------------|--------|--------|------------|----------------|---------------|
|                            | Watertight | Visual Defects  |        |        | Dimensions | Elongation (%) | Tensile (MPa) |
|                            |            | Critical Visual | Major  | Minor  |            | Pre Aging      | Pre Aging     |
| Sample Size :              | 300        | 300             | 300    | 300    | 80         | 60             | 60            |
| AQL Level :                | 1.5        | 1.5             | 2.5    | 4.0    | 2.5        | 2.5            | 2.5           |
| Failures Allowed per AQL : | 7          | 7               | 12     | 17     | 4          | 3              | 3             |
| Failures :                 | 0          | 0               | 0      | 0      | 0          | 0              | 0             |
| Inspection Results :       | Accept     | Accept          | Accept | Accept | Accept     | Accept         | Accept        |
| <b>Averages:</b>           |            |                 |        |        |            | 586            | 40.82         |

Test Methods : Water tight test ASTM D 5151, EN 455-1, Elongation and Tensile ASTM D 412, ASTM D 6319, EN 455-2, Dimension ASTM D 6319, EN 455-2

| Particle Test Data**    |            |            |                    |                                   |
|-------------------------|------------|------------|--------------------|-----------------------------------|
| Particle Size (µm)      | Min        | Max        | Standard Deviation | Average Particles/cm <sup>2</sup> |
| 0.5 - 1.0               | 642        | 814        | 87                 | 734                               |
| 1.0 - 2.0               | 56         | 91         | 18                 | 73                                |
| 2.0 - 5.0               | 13         | 22         | 4                  | 18                                |
| 5.0 - 10.0              | 1          | 3          | 1                  | 2                                 |
| 10.0 - 20.0             | 0          | 1          | 0                  | 1                                 |
| >20                     | 0          | 0          | 0                  | 0                                 |
| <b>Total per Sample</b> | <b>757</b> | <b>885</b> | <b>65</b>          | <b>828</b>                        |

Test Method : IEST-RP-CC005.4

| Extractable Ion Test Data** |                            |  |   |                               |   |  |       |
|-----------------------------|----------------------------|--|---|-------------------------------|---|--|-------|
|                             | <u>Anions Results</u>      |  |   |                               |   |  |       |
|                             | Fluoride<br>F <sup>-</sup> | Chloride<br>Cl <sup>-</sup>              | Nitrite<br>NO <sub>2</sub> <sup>-</sup> | Bromide<br>Br <sup>-</sup>    | Nitrate<br>NO <sub>3</sub> <sup>-</sup> | Phosphate<br>PO <sub>4</sub> <sup>3-</sup> |       |
| µg/g glove                  | 0.576                      | 30.181                                   | 1.729                                   | 1.729                         | 5.934                                   | 2.882                                      | 4.627 |
| µg/cm <sup>2</sup>          | 0.003                      | 0.181                                    | 0.011                                   | 0.011                         | 0.035                                   | 0.017                                      | 0.028 |
|                             | <u>Cations Results</u>     |  |   |                               | <u>Trace Element Results</u>            |  |       |
|                             | Sodium<br>Na <sup>+</sup>  | Ammonium<br>NH <sub>4</sub> <sup>+</sup> | Potassium<br>K <sup>+</sup>             | Magnesium<br>Mg <sup>+2</sup> | Calcium<br>Ca <sup>+2</sup>             | Zinc<br>Zn                                 |       |
| µg/g glove                  | 2.884                      | 1.913                                    | 1.975                                   | 1.153                         | 20.178                                  | 2.48                                       |       |
| µg/cm <sup>2</sup>          | 0.017                      | 0.012                                    | 0.012                                   | 0.007                         | 0.121                                   | 0.02                                       |       |

Test Method : IEST-RP-CC005.4

\*Registered Trademark or Trademark of Kimberly-Clark Corporation or its affiliates. Copyright 2001 Kimberly-Clark Corp.

This document is intended for customer use only. Any disclosure, copying, distribution, or other use of this document is strictly prohibited.

Review By :

- 15 May 2023  
 ( QA Sr. Manager )

# Test Method for Analyzing Liquid Particle Counts

This test method is used to analyze the mobile particle contaminants from cleanroom gloves.

## 1. Scope

- 1.1. The test method covers the average particulate contamination found on gloves designated for cleanroom applicability.
- 1.2. The average contaminant concentration will be reported in particles per cm<sup>2</sup> in two ways:
  - 1.2.1. By size grouping, 0.5 to 1.0 microns, 1.0 to 2.0 microns, 2.0 to 5.0 microns, 5.0 to 10.0 microns, 10.0 to 20.0 microns, greater than 20.0 microns, and a total particle count greater than 0.5 microns.
  - 1.2.2. Statistical analysis of each grouping consisting of Minimum Value, Maximum Value, Standard Deviation, and Average Value, for each group of individual gloves.
- 1.3. The safe and proper use of gloves is beyond the scope of this test method.
- 1.4. This test method does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this Test Method to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

## 2. Referenced Documents

- 2.1. IEST-RP-CC005.3 Recommended Practice for Gloves and Finger Cots Used in Cleanrooms and Other Controlled Environments
- 2.2. Work Instruction

## 3. Apparatus

- 3.1. Analytical Balance, capable of readability and repeatability to 0.1 mg
- 3.2. Particle Measuring Systems CLS-900 Liquid Particle Counting System
- 3.3. 2000 mL glass beaker or 1000mL glass conical flask
- 3.4. Stainless Steel Forceps, 10" length
- 3.5. 250 ml Volumetric Flask
- 3.6. 500 ml Volumetric Flask
- 3.7. High Purity Deionized Water System, capable of producing 18.2 MOhm quality water
- 3.8. Point of Use Filter, 0.2 micron size
- 3.9. Orbital Shaker, 3/4" orbit, capable of 200 rpm
- 3.10. Circular Die, 1.5 inch diameter, calibrated

## 4. Procedure

### 4.1. Test Preparation

- 4.1.1. Prior to extraction, all Erlenmeyer flasks will be cleaned no less than five times with high purity deionized water filtered to 0.2 microns at point of use.
- 4.1.2. All related equipment (forceps, volumetric flasks, etc.) must be rinsed with high purity deionized water prior to use.

### 4.2. Extraction

- 4.2.1. Randomly pull a glove from the package.
- 4.2.2. Place glove finger-first into the one liter Erlenmeyer flask and hold open by cuff using the rinsed forceps.
- 4.2.3. Empty into the inside of the glove 500 ml high purity filtered deionized water.
- 4.2.4. Allow the glove to settle into the Erlenmeyer flask.
- 4.2.5. Place an additional 250 ml high purity filtered deionized water over the glove within the Erlenmeyer flask.
- 4.2.6. Allow the Erlenmeyer flask with glove to agitate on the shaker for 10 minutes  $\pm$  10 seconds at a rate of 150 rpm  $\pm$  10 rpm.
- 4.2.7. Using clean tongs, immediately remove the glove from the container. Drain any trapped liquid into the beaker by manipulating the fingers on the glove, with the tongs
- 4.2.8. Dispose of the glove.
- 4.2.9. Repeat the extraction two additional times to complete the set.
- 4.2.10. Prepare a process blank, using all the steps in section 4.2, without placing the glove in the Erlenmeyer flask.

#### 4.3. Measurement

4.3.1. Follow the Work Instruction for the Liquid Particle Counter for analyzing the solutions.

#### 4.4. Glove Surface Area

4.4.1. Pull three gloves from the production package and weigh to the nearest 0.1 mg.

4.4.2. Record as A.

4.4.3. Cut the 3 gloves with square die (5X5 cm.) by wheel cutter at palm. This will give you six cut-out sections.

4.4.4. Weight the six cut-out sections. Record this as B.

4.4.5. Calculate the surface area of the glove using the following equation :

$$\frac{A \times 5 \times 5 \times 4}{B}$$

#### 5. Calculations

5.1. Calculate counts/cm<sup>2</sup> by channel size using the following equation:

$$\frac{(\text{Sample (counts/mL)} - \text{Blank (Counts/mL)}) \times \text{Extraction volume (mL)} \times \text{DF}}{\text{Surface area (in cm}^2\text{)}}$$

5.2. Total Counts/cm<sup>2</sup> : =  $\sum$  *AllChannelSizes*

#### 6. Reporting

6.1. The final report should include the Lot Number, Batch number, Product Description, Part Number, and any other pertinent information about the sample, as well as the final calculated counts/cm<sup>2</sup> by channel size and a total counts/cm<sup>2</sup> greater than 0.5 microns.

6.2. Statistics will be calculated and reported on sample sizes greater than three.

## Test Method for Analyzing Extractables

This test method is used to analyze the soluble ionic extractable contaminants from cleanroom gloves.

### 1. Scope

- 1.1. The test method covers the average ionic contamination found on gloves designated for cleanroom applicability.
- 1.2. The average contaminant concentration will be reported in one of two ways:
  - 1.2.1. Micrograms of ionic contaminant per gram of glove weight (ug/g), also described as ppm.
  - 1.2.2. Micrograms of ionic contaminant per square centimeter of glove area (ug/cm<sup>2</sup>)
- 1.3. This test method does not cover contaminants that are insoluble in water, or organic macromolecules.
- 1.4. The safe and proper use of gloves is beyond the scope of this test method.
- 1.5. This test method does not purport to address all of the safety concerns, if any, associated with its use. It is the responsibility of the user of this Test Method to establish appropriate safety and health practices and determine the applicability of regulatory limitations prior to use.

### 2. Referenced Documents

- 2.1. IEST-RP-CC005.2 Recommended Practice for Gloves and Finger Cots Used in Cleanrooms and Other Controlled Environments.
- 2.2. Work Instruction WI 10-05-26, Work Instruction for Performing Ion Chromatography Analysis of Gloves

### 3. Apparatus

- 3.1. Analytical Balance, capable of readability and repeatability to 0.1 mg
- 3.2. Ion Chromatograph
- 3.3. Extraction Containers, 1 liter capacity, HDPE with screw type lids
- 3.4. Stainless Steel Forceps, 10" length
- 3.5. 500 ml Volumetric Flask
- 3.6. High Purity Deionized Water System, capable of producing 18.0 MOhm quality water
- 3.7. Point of Use Filter, 0.1 micron size
- 3.8. Circular Die, 1.5 inch diameter, calibrated

### 4. Procedure

#### 4.1. Test Preparation

- 4.1.1. Prior to extraction, all extraction containers will be cleaned using high purity deionized water high purity deionized water filtered to 0.2 microns at point of use.
- 4.1.2. All related equipment (forceps, volumetric flasks, etc.) must be rinsed with high purity de-ionized water prior to use.

#### 4.2. Extraction

- 4.2.1. Randomly pull a glove from the package.
- 4.2.2. Place glove finger-first into the one liter Erlenmeyer flask and hold open by cuff using the rinsed forceps.
- 4.3. Empty into the inside of the glove approximately 250 ml high purity filtered deionized water.
- 4.4. Allow the glove to settle into the extraction container.
- 4.5. Pour remaining 250 ml high purity filtered deionized water over the glove within the extraction container.
- 4.6. Place the lid upon the container and seal tightly.
- 4.7. Gently swirl the container to ensure that all surfaces of the glove are wetted.
- 4.8. Allow the glove to extract in the deionized water for at least 10 minutes, but no longer than 11 minutes.
- 4.9. Remove the glove by the fingers, allowing most of the water trapped in the fingers to drain back in to the extraction container.
- 4.10. Dispose of the glove.
- 4.11. Repeat extraction two additional times to complete the set.
- 4.12. Prepare a sample blank, using all the steps in section 2, without placing the glove in the extraction container.

4.13. Measurement

4.13.1. Follow the guidelines for the Ion Chromatograph for analyzing aqueous solutions.

4.14. Glove weight and surface area

4.14.1. Pull three gloves from the production package and weigh to the nearest 0.1 mg.

4.14.2. Record as A.

4.14.3. Cut the 3 gloves with square die (5X5 cm.) by wheel cutter at palm. This will give you six cut-out sections.

4.14.4. Weight the six cut-out sections. Record this as B.

4.14.5. Calculate the surface area of the glove using the following equation :

$$\text{Surface area} = \frac{A \times 5 \times 5 \times 4}{B}$$

5. Calculations

5.1. Once the data output from the Chromatograph has been reviewed for errors, calculate the following:

$$5.1.1. \text{ ug/g (ppm) contamination: } = \frac{(\text{AnalyteConc.}) * (500\text{ml})}{\text{GloveWeight}}$$

$$5.1.2. \text{ ug/cm}^2 \text{ contamination: } = \frac{(\text{AnalyteConc.}) * (500\text{ml})}{\text{SurfaceArea}}$$

6. Reporting



6.1. The final report should include the Lot number, Batch number, Product description, Part number, and any other pertinent information about the sample, as well as the final calculated contaminant concentration in ug/g and ug/cm<sup>2</sup>.



# Case Label

## G3 NxT Nitrile Gloves

**M 7.0-7.5**

 100 x  10 = 1000  
12" (30.5cm)

- EN G3 NxT Nitrile Gloves
- FR Gants en nitrile G3 NxT
- ES G3 Guantes de nitrilo G3 NxT
- DE G3 NxT Nitrilhandschuhe
- NL G3 NxT nitril handschoenen
- IT G3 Guanti in nitrile NxT
- RU G3 NxT Нитриловые перчатки
- UA Рукавички нітрилові G3 NxT
- PT Luvas de nitrilo NxT G3
- KO G3 NxT 니트릴 장갑
- ZH G3 NxT 丁腈手套
- JA G3 NxT ニトリル手袋

EN ISO 374-1:2016+A1:2018/Type B



EN ISO 374-5:2016



**62992** **40**

**LOT** XXXXXX-XXXXXXXXXX

Lot Number  
Номер партии  
製造番号

 MM-YYYY  
Date of Manufacturing  
Дата производства  
製造年月

 YYYY-MM  
Expiration Date  
Использовать до  
使用期限

CE 0123 EAC  
UK 0168 TP TC 019/2011  
CA 0168

AQL 1.5  
LM62992400L-00



1 00 36000 62992 4



# Polybag

## KIMTECH™



### G3 NxT Nitrile Gloves 12" Ambidextrous / 30.5 cm

- XS (5.5) = 62990
- S (6.0-6.5) = 62991
- M (7.0-7.5) = 62992
- L (8.0-8.5) = 62993
- L+ (8.5-9.0) = 62995
- XL (9.0-10.0) = 62994

- ④ G3 NxT Nitrile Gloves, Ambidextrous 12"/30.5cm
- ④ Gants en nitrile G3 NxT, Ambidextre 12"/30.5cm
- ④ G3 Guantes de nitrilo G3 NxT, Ambidiestro 12"/30.5cm
- ④ G3 NxT Nitrilhandschuhe, Beidhändig 12"/30.5cm
- ④ G3 NxT nitril handschoenen, Ambidexter 12"/30.5cm
- ④ G3 Guanti in nitrile NxT, Ambidestri 12"/30.5cm
- ④ G3 NxT Нитриловые перчатки, Амбидекстральные 12"/30.5cm
- ④ Рукавички нитриловые G3 NxT, Одноразовые для обеих рук 12"/30.5cm
- ④ Luvas de nitrilo NxT G3, Ambidestra 12"/30.5cm
- ④ G3 NxT 니트릴 장갑, 양손용 12"/30.5cm
- ④ G3 NxT ニトリル手袋, 左右兼用 12"/30.5cm

- ④ For the Cleanroom Environment • For Industrial Use Only
- ④ Pour l'environnement contrôlé de salle blanche • Pour usage industriel uniquement
- ④ Para el entorno controlado de sala blanca • Sólo para uso industrial
- ④ Für die kontrollierte Reinraumumgebung • Nur für den industriellen Gebrauch
- ④ クリーンルーム制御環境用・産業用専用

®™ Trademarks of Kimberly-Clark Worldwide, Inc. or its affiliates. © KCCWW  
®™ Marques de commerce de Kimberly-Clark Worldwide, Inc. ou de ses filiales. © KCCWW  
® Запатентованный товарный знак Кимберли-Кларк Ворлдвайд, Инк. или его аффилированных лиц. © KCCWW  
® Запатентованный знак для товарів пошуку Кимберлі-Кларк Ворлдвайд, Інк. або його аффіліованих осіб. © KCCWW  
Manufactured / Произведено в Европе: Kimberly-Clark Europe Limited, Watton Oaks, Dorking Road, Taplow, Surrey, KT20 7NS, UK (Бельгия/произведено в Бельгии/Бельгия) www.kcpprofessional.com +44 (0) 1707 736000  
Made in Thailand / Fabriqué en Thaïlande / Fabricado en Tailandia / Произведено в Таиланде / ผลิตในประเทศไทย  
Manufacturing process: Sterilized powder  
Сайт/сайт: Medline и/или Сайнтетик Тайланд, 200 Мо. 8, Наканканан Роуд, Тхайбор Парк, Амур Сидро, 90/00 Советск, Тайланд  
Сайт/сайт: Medline и/или Сайнтетик Тайланд, 200 Мо. 8, Наканканан Роуд, Тхайбор Парк, Амур Сидро, 90/00 Советск, Тайланд  
Distributed in the U.S. by Kimberly-Clark Global Sales, LLC, Roswell, GA 30075-2199  
Distributed in Canada by/ Distribuidor en Canadá por Kimberly-Clark Inc., Mississauga, Ontario L5B 9H5  
Distributed in Australia by: Kimberly-Clark Australia Pty. Limited, 100 Arthur Street, North Sydney, NSW 2060  
EU Importer Kimberly-Clark B.V., Copernicuslaan 35, 6719 BH Ede, Netherlands  
Уповноважена організація щодо продажів продукції від оптовика на території України ТОВ «Кімберлі-Кларк Україна», 03038, м. Київ, вул. Мельникова 2/1, Україна / Уповноважений оптовик в Україні: ООО «Кімберлі-Кларк Україна», Российская Федерация, 141600, Московская область, г. Ступино, ул. Орлова, владение 15, www.kcpprofessional.com/ru  
Distributed in New Zealand by: Kimberly-Clark New Zealand, Level 2, 123 Carter Gore Road, Newmarket, Auckland 1023, New Zealand


中國經銷商: 金豐利(中國)有限公司 上海南京路62號13樓 200002  
電: 400-620-1111  
Distributed in Hong Kong by: Kimberly-Clark (Hong Kong) Ltd., G.P.O. Box 6838, Hong Kong  
Tel: (852) 2355-6840 E-Mail: kcpn@kcc.com  
Distributed in India by: Kimberly-Clark Hygiene Products Private Limited  
Bublinghi, Plot No. P-5, MIDC Chakan, Phase II, Village-Khalanore, Taluka-Khat, Dist-Pune - India 410 501 E-Mail: customercare.india@kcc.com  
Distribuidor en Indonesia oleh: PT. Kimberly-Clark Indonesia The Prominence Tower Lantai 5, Jl. Jaker Sateia Barat No. 15, Kawasan Penunjanggangan Timur, Kacamatan Pinang, Kota Tangerang, Provinsi Banten 15143, Indonesia. E-Mail: kcp.indonesia@kcc.com  
Distribuidor en Malaysia oleh: Kimberly-Clark Trading (M) Sdn. Bhd., Tingkat 2, Meraya 2, Wisma AirFirst, Jalan SS87/15 (Jalan Stadium), Kelana Jaya, 47301 Petaling Jaya, Selangor Darul Ehsan, Malaysia  
E-Mail: Malaysia.kcp@kcc.com  
Distribuidor en Philippines sa Pilipinas ng: Kimberly-Clark Philippines, Inc.  
455 Compound, 48 Bonifacio St., Santa Cruz (East), Valenzuela City 1447, Philippines E-Mail: KCPPhil@kcc.com  
Distributed in Singapore by: Kimberly-Clark Singapore Pte. Ltd., 81 Tuas South Avenue B, Singapore  
137159, E-Mail: Singapore.kcp@kcc.com  
台灣分公司: 金豐利信託商會金百利克拉克股份有限公司台灣分公司  
台北市 310 信義區信義路五段 8 號 8 樓 E-Mail: tp@kcp.com.tw  
Selling in Thailand by: KCP (Thailand) - KCP (Thailand) Co., Ltd. 323  
ถนนพหลโยธิน แขวงจันทบุรี เขตจันทบุรี กรุงเทพฯ 10500 ประเทศไทย E-Mail: KCPThailand@kcc.com  
06551110011 06551110011 06551110011 06551110011 06551110011  
www.kcpprofessional.com



Place Label Here

# KIMTECH™

# KDF Artwork





## G3 NxT Nitrile Gloves 12" / 30.5cm - Ambidextrous



### EN G3 NxT Nitrile Gloves

- 12"/30.5cm Length
- Ambidextrous
- Textured
- Not Made With Natural Rubber Latex
- For the Cleanroom Environment
- For Industrial Use Only

**NOTICE:** THIS INSERT SHOULD BE FURNISHED OR MADE AVAILABLE TO THE USERS OF THESE GLOVES AS A SAFETY PRECAUTION.

This is a **Category III PPE** certified according to **Regulation (EU) 2016/425** and to **Regulation (EU) 2016/425** as brought in the UK law and amended. **Risk: Gloves offer protection against chemicals (Splash) and micro-organisms.** This information does not reflect the actual duration of protection in the workplace and the differentiation between mixtures and pure chemicals. The chemical resistance has been assessed under laboratory conditions from samples taken from the palm only and relates only to the chemical tested. It can be different if the chemical is used in a mixture. Degradation results indicate the change in puncture resistance after exposure to the challenge chemical. It is recommended to check that the gloves are suitable for the intended use because the conditions at the workplace may differ from the type test depending on temperature, abrasion and degradation. When used, protective gloves may provide less resistance to the dangerous chemical due to changes in the physical properties. Movements, snagging, rubbing, degradation caused by the chemical contact etc. may reduce the actual use time significantly. For corrosive chemicals, degradation can be the most important factor to consider in selection of chemical resistant gloves. The penetration resistance has been assessed under laboratory conditions and relates only to the tested specimen. Before usage, inspect the gloves for any defect or imperfections. Refer to enclosed donning and doffing instructions. For single use only. Store in a cool dry place. Dispose of according to local regulations. A list of substances known to cause allergies can be supplied on demand.

**CONTACT US:** If you have any questions about this product, call the manufacturer at (US) 1-800-255-6401 (EU) +44(0) 1737 736000 (AP) +603 7807 8210

### FR Gant nitrile G3 NxT

- Longueur 12"/30,5cm
- Ambidextres
- Texturés
- Ne contient pas de latex de caoutchouc naturel
- Pour les environnements de salles blanches
- Utilisés à des fins commerciales seulement

**AVIS :** PAR MESURE DE SÉCURITÉ, CET ENCART DOIT ÊTRE FOURNI AUX UTILISATEURS DE CES GANTS OU ÊTRE À LEUR DISPOSITION.

**Il s'agit d'un EPI de catégorie III certifié en vertu du Règlement (UE) 2016/425. Risque :** Les gants offrent une protection contre les produits chimiques (éclaboussures) et les micro-organismes.

Les présents renseignements ne reflètent pas nécessairement la durée réelle de la protection en milieu de travail ni la différence entre les mélanges et les produits chimiques purs. La résistance aux produits chimiques a été évaluée en laboratoire à l'aide d'échantillons prélevés dans la paume seulement et ne concerne que le produit chimique testé. Les résultats peuvent être différents si le produit chimique est utilisé dans un mélange. Les résultats relatifs à la dégradation indiquent le changement dans la résistance à la perforation après l'exposition au produit chimique. Il est recommandé de s'assurer que les gants conviennent à l'usage prévu, car les conditions en milieu de travail peuvent différer de celles de l'essai type, selon la température, l'abrasion et la dégradation. Lorsqu'ils sont utilisés, les gants peuvent fournir moins de résistance aux produits chimiques dangereux en raison de changements dans les propriétés physiques. Les mouvements, les déchirures, le frottement et la dégradation causée par le contact avec les produits chimiques, etc. peuvent considérablement réduire la durée réelle d'utilisation. Dans le cas des produits chimiques corrosifs, la dégradation peut être le facteur le plus important à considérer lorsque vient le temps de choisir des gants résistants aux produits chimiques. La résistance à la pénétration a été évaluée en laboratoire et ne concerne que l'échantillon testé. Inspecter les gants avant l'utilisation pour vérifier qu'ils ne comportent pas de défauts ou d'imperfections. Consulter les instructions d'emploi pour enlever et retirer les gants. Usage unique seulement. Ranger dans un endroit frais et sec. Mettre au rebut conformément aux règlements municipaux. Une liste des substances connues pour provoquer des allergies peut être fournie sur demande.

**NOUS CONTACTER :** Pour tout renseignement concernant ce produit, appeler le fabricant au (États-Unis) 1-800-255-6401 (Europe) +44(0) 1737 736000 (Asie-Pacifique) +603 7807 8210

### DE G3 NxT Nitrilhandschuhe

- 12"/30,5 cm Länge
- Beidhändig
- Texturiert
- Ohne Naturkautschuklatex
- Für Reinraumumgebungen
- Nur für die industrielle Verwendung

**HINWEIS:** DIESE PACKUNGSBEILAGE SOLLTE ANWENDERN ALS SICHERHEITSVORKEHRUNG AUSGEHÄNDIGT ODER ZUR VERFÜGBARKEIT GESTELLT WERDEN.

**Dies ist ein nach Kategorie III PSA zertifiziertes Produkt gemäß Verordnung (EU) 2016/425. Risiko:** Handschuhe bieten Schutz gegen Chemikalien (Spritzer) und Mikroorganismen.

Diese Informationen spiegeln nicht die tatsächliche Schutzdauer am Arbeitsplatz und die Differenzierung zwischen Mischungen und reinen Chemikalien wider. Die Chemikalienbeständigkeit wurde unter Laborbedingungen durch ausschließlich an

der Handfläche entnommene Proben bestimmt und bezieht sich nur auf die geprüfte Chemikalie. Die Beständigkeit kann unterschiedlich sein, wenn die Chemikalie in einer Mischung verwendet wird. Degradationsergebnisse zeigen die Punktionsbeständigkeit nach Exposition gegenüber der Chemikalie an. Es wird empfohlen, die Eignung der Handschuhe für den vorgesehenen Verwendungszweck zu prüfen, da sich die Bedingungen am Arbeitsplatz von den Prüfbedingungen hinsichtlich Temperatur, Abnutzung und Zersetzung unterscheiden können. Schutzhandschuhe können bei der Verwendung aufgrund von Veränderungen der physikalischen Eigenschaften eine geringere Beständigkeit gegen die gefährliche Chemikalie aufweisen. Bewegungen, Verhakung, Reibung, durch den Kontakt mit Chemikalien verursachte Zersetzung usw. können die tatsächliche Verwendungszeit erheblich verringern. Bei korrosiven Chemikalien kann Zersetzung der wichtigste Faktor sein, der bei der Auswahl von chemikalienbeständigen Handschuhen zu berücksichtigen ist. Der Penetrationswiderstand wurde unter Laborbedingungen geprüft und bezieht sich nur auf die geprüfte Probe. Die Handschuhe vor der Verwendung auf Mängel oder Fehler prüfen. Nicht zur Wiederverwendung. Siehe beigefügte Anweisungen zum Anziehen und Ausziehen. An einem kühlen, trockenen Ort lagern. Gemäß den örtlichen Vorschriften entsorgen. Eine Liste der Stoffe, die bekanntermaßen Allergien auslösen, kann auf Anfrage geliefert werden.

**SO KONTAKTIEREN SIE UNS:** Bei Fragen zu diesem Produkt rufen Sie bitte den Hersteller an unter der Nummer (US) 1-800-255-6401; (EU) +44(0) 1737 736000; (AP) +603 7807 8210

### NL G3 NxT Nitril handschoenen

- 30.5cm/12 inch lang
- Ambidexter
- Getextureerd
- Niet gemaakt van natuurlijke rubberlatex
- Voor schone ruimtes
- Alleen voor industrieel gebruik

**WAARSCHUWING: DEZE BIJSLUITER DIENT ALS VEILIGHEIDSMAAATREGEL GEGEVEN TE WORDEN AAN OF TER BESCHIKING GESTELD TE WORDEN VAN DE GEBRUIKERS VAN DEZE HANDSCHOENEN.**

**Dit is een persoonlijk beschermingsmiddel van categorie III volgens Verordening (EU) 2016/425. Risico: Handschoenen bieden bescherming tegen chemische stoffen (spatten) en micro-organismen.**

Deze informatie is geen weerspiegeling van de werkelijke beschermingsduur in de werkomgeving en de differentiatie tussen mengsels en zuivere chemicaliën. De chemische weerstand is onder laboratoriumomstandigheden beoordeeld op grond van monsters genomen van alleen de palm en heeft alleen betrekking op het geteste chemische product. Het kan anders zijn als het chemische product in een mengsel wordt gebruikt. Verslechteringsresultaten geven de verandering in punctiebestendigheid na blootstelling aan de betreffende chemische stof aan. Het wordt aanbevolen te controleren of de handschoenen geschikt zijn voor het beoogde gebruik omdat de omstandigheden in de werkomgeving kunnen verschillen van de type test afhankelijk van temperatuur, schuring en afbraak. Bij het gebruik kunnen beschermende handschoenen minder weerstand bieden tegen het gevaarlijke chemische product vanwege veranderingen in de fysieke eigenschappen. Bewegingen, blijven haken, wrijven, afbraak veroorzaakt door contact met het chemische product etc. kunnen de werkelijke gebruiksduur aanzienlijk verminderen. Bij corrosieve chemische producten kan afbraak de belangrijkste factor zijn waarmee rekening moet worden gehouden bij de keuze van chemisch bestendige handschoenen. De weerstand tegen indringen is beoordeeld onder laboratoriumomstandigheden en heeft alleen betrekking op het geteste specimen. Controleer de handschoenen vóór gebruik op beschadiging of onvolkomenheden. Raadpleeg de bijgevoegde instructies voor aan- en uittrekken. Uitsluitend voor eenmalig gebruik. Op een koele, droge plaats bewaren. Afvoeren volgens de plaatselijke voorschriften. Een lijst van stoffen waarvan bekend is dat ze allergieën veroorzaken, is op aanvraag verkrijgbaar. **CONTACT MET ONS OPNEMEN:** Als u vragen hebt over dit product, kunt u de fabrikant bereiken op nr.: (Verenigde Staten) +1-800-255-6401 (Europa) +44(0) 1737 736000 (Azië-Pacifc) +603 7807 8210.

### IT G3 Guanti in nitrile NxT

- Lunghezza 12"/30,5 cm
- Ambidestri
- Ruvidi
- Non prodotto con lattice di gomma naturale
- Per camera bianca
- Solo per uso industriale

**AVVISO - QUESTO INSERTO DEVE ESSERE FORNITO O RESO DISPONIBILE COME MISURA DI SICUREZZA A COLORE CHE UTILIZZANO QUESTI GUANTI.**

**Questo prodotto è certificato come DPI di categoria III secondo il Regolamento (UE) 2016/425. Rischio: i guanti offrono protezione contro sostanze chimiche (schizzi) e microrganismi.**

Queste informazioni non riflettono la durata effettiva della protezione sul luogo di lavoro e la distinzione tra prodotti chimici miscelati e puri. La resistenza chimica è stata misurata in condizioni di laboratorio su campioni presi solo dal palmo della mano e si riferisce solo al prodotto chimico testato. Può essere diverso se il prodotto chimico viene utilizzato in una miscela. I risultati della degradazione indicano il cambiamento nella resistenza alle perforazioni dopo l'esposizione a sostanze chimiche. Si consiglia di controllare che i guanti siano idonei per l'uso previsto poiché le condizioni del luogo di lavoro possono differire dal tipo di test a seconda della temperatura, abrasione e degradazione. Quando utilizzati, i guanti di protezione possono fornire meno resistenza ai prodotti chimici pericolosi a causa di cambiamenti delle proprietà fisiche. Il tempo effettivo di utilizzo può essere ridotto significativamente a causa di movimenti, sfilacciamento, strofinamento o degradazione dovuti al contatto con prodotti chimici, ecc. In caso di contatto con prodotti chimici corrosivi, il fattore più determinante da considerare nella scelta di guanti resistenti ai prodotti chimici è la resistenza alla degradazione. La resistenza alla penetrazione è stata misurata in condizioni di laboratorio e riguarda solo il campione testato. Prima dell'uso, ispezionare i guanti per verificare l'assenza di difetti o imperfezioni. Consultare le istruzioni allegate per indossare e togliere il prodotto. Solo monouso. Conservare in un luogo asciutto e fresco. Smaltire in conformità alle disposizioni locali. Un elenco di sostanze note come causa di allergie può essere fornito su richiesta.

**PER CONTATTARCI -** Per chiarimenti circa questo prodotto rivolgersi al produttore al numero 1-800-255-6401 (USA), +44(0) 1737 736000 (Europa), +603 7807 8210 (Asia Pacifico).


### ES Guantes de nitrilo G3 NxT

- 12 pulg./30,5 cm de largo
- Ambidiestro
- Texturizados
- No fabricado con látex de goma natural
- Para entornos de sala blanca
- Solo para uso industrial

**AVISO: COMO MEDIDA DE SEGURIDAD, ESTE ENCARTO SE DEBE ENTREGAR O PONER A DISPOSICIÓN DE LOS USUARIOS DE ESTOS GUANTES**

### REF G3 NxT

- XS (5.5) = 62990
- S (6.0-6.5) = 62991
- M (7.0-7.5) = 62992
- L (8.0-8.5) = 62993
- L+ (8.5-9.0) = 62995
- XL (9.0-10.0) = 62994



EN ISO 374-4:2016+A1:2018/Type B



EN ISO 374-5:2016



- EN Tested for Watertightness, Chemical Permeation and Chemical Degradation
- FR Testés pour l'imperméabilité, la perméation de produits chimiques et la dégradation chimique
- ES Sometidos a pruebas de estanqueidad, permeación química y degradación química
- DE Geprüft auf Wasserdichtigkeit, Permeation von chemischen Substanzen und chemische Abbaubarkeit
- RU Прошли испытания на водонепроницаемость, проницаемость для химических веществ и химическое разрушение
- UA Прошли випробування на водонепроникність і захист від проникнення та стійкість до хімічних речовин
- IT Testato per tenuta all'acqua, permeazione ai prodotti chimici e degradazione chimica
- NL Getest op waterdichtheid, permeatie door chemicaliën en afbraak door chemicaliën
- HU Tesztelt vízárálló képesség, kémiai áthatolhatóság és kémiai degradáció

- EN Resistance to bacteria and fungi: PASS
- FR Résistance to bacterias: PASS
- ES Resistencia aux bacterias et aux champignons: REUSI
- DE Resistenz aux virus: REUSI
- RU Resistencia a bacterias y hongos: SUPERADA
- UA Resistencia a los virus: SUPERADA
- IT Resistenz gegenüber Bakterien und Pilzen: Bestanden
- DE Resistenz gegenüber Viren: Bestanden
- RU Устойчивость к бактериям и грибок: УДОВЛЕТВОРИТ ТРЕБОВАНИЯМ
- UA Устойчивость к вирусам: УДОВЛЕТВОРИТ ТРЕБОВАНИЯМ
- IT Stitività do bacterii i grimbii: ZĂDOVOLĂNĂȚY VIMOGRAM
- IT Stitività do virus: ZĂDOVOLĂNĂȚY VIMOGRAM
- IT Resistenza a batteri e muffe: CONFORME
- IT Resistenza ai virus: CONFORME
- DE Weerstand tegen bacteriën en schimmels: GESLAAGD
- DE Weerstand tegen virussen: GESLAAGD
- HU Ellenlállás baktériumoknak és gombáknak: TELJESÍTVÉ
- HU Ellenlállás vírusoknak: TELJESÍTVÉ

- EN Single Use Only.
- FR Usage unique seulement
- ES Úsese una sola vez
- DE Nur zur einmaligen Verwendung
- RU Только для одnorазового применения
- UA Виключно для одnorазового застосування
- IT Solo monouso
- NL Uitsluitend voor eenmalig gebruik
- HU Egyszer használatos

- EN Protect from Heat and Radioactive Sources
- FR À protéger contre les sources de chaleur et radioactives
- ES Proteger contra fuentes de calor y radioactividad
- DE Vor Hitze und radioaktiven Strahlen schützen
- RU Беречь от нагрева и источников радиоактивного излучения
- UA Оберегати від нагрівання і джерел радіоактивного випромінювання
- IT Protegge dal calore e dalle sorgenti radioattive
- DE Beschermen tegen warmte en radioactieve bronnen
- HU Védje a hőtől és a radioaktív sugárzástól

- EN Keep Dry
- FR Conservar au sec
- ES Mantener secos
- DE Trocken halten
- RU Хранить в сухом месте
- UA Зберігати в сухому місці
- IT Mantenerne asciutto
- DE Droog bewaren
- HU Tartsa szárazon

### G3 NxT Nitrile Gloves

| Chemical                   | Permeation Test<br>EN ISO 374-1:2016+A1:2018 |                   | Degradation Test<br>EN ISO 374-4:2019 |                     |
|----------------------------|--|-------------------|---------------------------------------|---------------------|
|                            | Breakthrough Time (min.)                     | Performance Level | Performance Level %                   | Performance Level % |
| Sodium Hydroxide, 40% (K)  | >240   | Class 5           | -                                     | -14,5%              |
| Hydrogen Peroxide, 30% (P) | >120   | Class 4           | -                                     | 55,3%               |
| Formaldehyde, 37% (T)      | >480   | Class 6           | -                                     | 18,8%               |

EN ISO 21420:2020 Dexterity Classification = 5



Certificates available from [www.kimtech.com/certificates](http://www.kimtech.com/certificates)

EU and UK Declarations of Conformity available at: [www.kimtech.eu](http://www.kimtech.eu)

